

Fuchsia Carpet Tiles

1st June 2008

Warranty

10 years subject to Flooring Industries Conditions

Construction.

1/10th Gauge tufted loop Polyamide Antron R 6.6

Total Weight.

4.655 kgs sq. mt. (Nom)

Pile Weight.

850 Gms sq.mt. (Nom)

Backing.

Bitumen with Glass fibre

Dimensions.

Pile Height 4.7 mm(Nom), Total Height 8.0mm (Nom), Tile size 50cm x 50cm (Nom)

Dimensional Stability.

EN989. Max -0.2%

Colour Fastness.

EN ISO 105-B02/ x12/ E01

Light: 5 Water: 4-5, Rubbing: 4-5

Static. Permanently antistatic: PrEN 1815 <2Kv

Surface Resistance

BS ISO/DIS 10965: 1998 (2005) 10⁹ohms.

Flammability.

EN 13501-1BF-S1 Less than 25mm flame spread on an incline burner. Maximum results achievable for a textile floorcoverings. "1" Best smoke emission result

Comfort.

EN1307 Luxury rating LC2

Usage.

EN1307: 3 Commercial Use

Castor Test.

En1307 rating 2.8Class A continuous use

Acoustic.

ISO 140-8 23db, ISO 354 Request full results

Thermal Resistance

ISO 8354 – 0,051qm K/W:0.079 qm K/W, Suitable for Underfloor Heating

Installation

Install to BS5325, CFA: best practice guide. Broadloom or Tessellated

We reserve the right to improve and change the specification of the product without notification